



URAI PAINTS  
[www.urpaints.com](http://www.urpaints.com)

# ATM Orange Primer QD no. 1264

Bulletin no. ....

Description	A special modified alkyd resin which developed for long lasting protection on metal or steel. It characterized with good adhesion, quick drying and excellent property for anti-rust.																																										
Application	Suitable to be using as primer for steel or metal surfaces such as handrail, grills for windows, curved steel, machines, etc.																																										
Technical Data	<table><tr><td>Product type</td><td>:</td><td colspan="2">Alkyd resin</td></tr><tr><td>Appearance</td><td>:</td><td colspan="2">Viscous liquid in orange colour.</td></tr><tr><td>Film type</td><td>:</td><td colspan="2">Egg shell matt</td></tr><tr><td>Specific Gravity (water = 1)</td><td>:</td><td colspan="2">1.7 – 1.8</td></tr><tr><td>Viscosity</td><td>:</td><td colspan="2">95 – 100 KU at 25 °C</td></tr><tr><td>Application tools</td><td>:</td><td colspan="2">Brush, roller</td></tr><tr><td>Diluent</td><td>:</td><td colspan="2">ATM Enamel Thinner</td></tr><tr><td>Drying time at 25 °C</td><td></td><td colspan="2"></td></tr><tr><td>- Dry to touch</td><td>:</td><td colspan="2">1 – 2 hours</td></tr><tr><td>- Dry to recoat</td><td>:</td><td colspan="2">6 - 8 hours.</td></tr></table>			Product type	:	Alkyd resin		Appearance	:	Viscous liquid in orange colour.		Film type	:	Egg shell matt		Specific Gravity (water = 1)	:	1.7 – 1.8		Viscosity	:	95 – 100 KU at 25 °C		Application tools	:	Brush, roller		Diluent	:	ATM Enamel Thinner		Drying time at 25 °C				- Dry to touch	:	1 – 2 hours		- Dry to recoat	:	6 - 8 hours.	
Product type	:	Alkyd resin																																									
Appearance	:	Viscous liquid in orange colour.																																									
Film type	:	Egg shell matt																																									
Specific Gravity (water = 1)	:	1.7 – 1.8																																									
Viscosity	:	95 – 100 KU at 25 °C																																									
Application tools	:	Brush, roller																																									
Diluent	:	ATM Enamel Thinner																																									
Drying time at 25 °C																																											
- Dry to touch	:	1 – 2 hours																																									
- Dry to recoat	:	6 - 8 hours.																																									
Painting System	<div>Surface preparation :</div> <p>Make sure the surface to be painted is free from dust, dirt, grease, waxy contaminant and loose particles. Rust or millscales should be removed.</p> <div>Primer coating :</div> <table><tr><td>- ATM Orange Primer QD. 1264</td><td>1 – 2 coats</td></tr><tr><td>- ATM Alkyd Enamel</td><td>2 – 3 coats</td></tr></table>			- ATM Orange Primer QD. 1264	1 – 2 coats	- ATM Alkyd Enamel	2 – 3 coats																																				
- ATM Orange Primer QD. 1264	1 – 2 coats																																										
- ATM Alkyd Enamel	2 – 3 coats																																										
Coverage	8 - 12 sq.m/ litre /coat																																										
Storage & Shelf life	Maximum 2 years in sealed container. Keep away from heat/ sparks/ open flames. No smoking. Keep container in a cool dry and well-ventilated place. Protect from direct sunlight. When not in use, keep container tightly closed and use again after correct storage.																																										
Safety, Health and Environment Information	Keep out of reach of children. Use only outdoors or in a well-ventilated area. Wear protective gloves, eye and face protection. Avoid contact with skin or eyes. Do not eat, drink or smoke when using this product. Vapours may cause drowsiness or dizziness. Wash thoroughly after handling. IF ON SKIN; Wash with plenty of soap and rinse skin with clean water. IF IN EYES, Rinse cautiously with water for several minutes. Do not empty into drains. Avoid release to the environment.																																										
Packing	0.875 Litres, 3.5 Litres and 17.5 Litres.																																										

**DISCLAIMER:** The above information provided herein is based on the present state of our knowledge and practical experience. Since the product is often used under different conditions beyond our control. We cannot guarantee anything but the quality of the product itself. All the rights are reserved to change the data without any notice.