



# Technical Data Sheet

**Product Name: 25000 Series**

**Open Cell EPDM – Black 2A0**

Physical Properties	Results	Test Method
Cell Structure	Open Cell	
Density (lb/ft <sup>3</sup> )	4.0 – 8.0	ASTM D1622
25% Compression Resistance (psi)	1 Max	ASTM D1056
50% Compression Set (%)	10 Max.	ASTM D1056
Water Absorption (%)	10 Max	ASTM C209
Tensile (psi)	15 Min.	ASTM D 412
Elongation (%)	100 Min.	ASTM D 412
Flammability MVSS302	Pass	MVSS302
Cold Crack @ -40°F	Pass	ASTMD1056
Ozone Resistance	No Crack	ASTM 1171
Service Temperature	-70 to 250F	ASTM D1171
R-Value (per inch)	4.2	ASTM C177

The data information is provided as a technical service and are subject to change without notice. To the extent the information is derived from sources other than ACT, ACT is substantially, if not wholly, relying upon the other source(s) to provide accurate information. Information provided as a result of ACT's own technical analysis and testing is accurate to the extent of our knowledge and ability, using effective standardized methods and procedures. Each user of these products, or information, should perform their own tests to determine the safety, fitness and suitability of the products, or combination of products. Since ACT cannot control the end use of this product, ACT does not guarantee that the user will obtain the same results as published in this document.