



Technical Data Sheet

Product Name: AF-30030K

#2 Density, 0.118 IXPE - FR

Tests Performed	Unit	Typical Results	Test Method
Tear Strength (M/CM)	N	4.94 / 3.68	GB/T528
Tensile Strength (M/CM)	MPa	0.45 / 0.34	GB/T528
Elongation (M/CM)	%	103.5 / 88.6	GB/T528
Thickness	mm	2.9 - 3.1 (0.114" - 0.122")	
Expansion Time (Density)	Times	29.4 - 30.2 (#2.06 - 2.12)	
Hardness		25 - 26	Shore C/1S
Cross Direction Tensile Strength (M/CM)	N/mm	2.16 / 1.46	
FR Grade		HF-1	UL 94

All data is typical and not to be considered specific values. ACT cannot predict or control the different conditions under which this information and our products may be applied. Each user of these products, or information, should perform their own tests to determine the safety, fitness, and suitability of the products, or combination of products, for any foreseeable purposes, applications and uses by the user and by any third party to which the user may convey the products. ACT does not guarantee that the user will obtain the same results as published in this document. The data and information is provided as a technical service, and the data and information are subject to change without notice.